


DESCRIPTION	Standard	Requirement	Units	Results
Dry-Tex System				
Eco-fit System				
<b>PRODUCT DESCRIPTION</b>				
Surface treatment	-	-	-	Triple-Action Protectsol®
Surface complex	-	-	-	D-Max™
Foam	-	-	-	-
Thickness	EN 428	-	mm	2.1
Weight	EN 430	-	kg/m <sup>2</sup>	2.9
Length	EN 426	-	lm	30 Max
Width	EN 426	-	lm	1.5
<b>SPORT PROPERTIES</b>				
Shock absorption	EN 14808	≥25	%	-
Vertical deformation	EN 14809	≤3.5	mm	-
Energy return	NF P 90 203	≥ 0.31	m/s	-
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
<b>TECHNICAL CHARACTERISTICS</b>				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
<b>CLASSIFICATION</b>				
Fire	EN 13501-1	-	-	Bfl-s1
Special treatment	-	-	-	Sanosol®
<b>CE MARKING</b>				
	EN 14 904 :2006	-	-	Fire  Sliding Coefficient Abrasion Resistance Resistance to roaling load